

Testing Report	Security website: www.fcl-sz.org.cn Security code: 7167787160	
Report No: ZFLJ2647747A	Page 1 of 3	



Applicant Information

Applicant Name : CONOR SKANDINAVIA AS

Applicant Address : Morteveien 6, 1481 Hagan, Norway

Manufacturer

Sample Information

: FASHION DUST MASK (NON-MEDICAL USE) Sample Description

Sample Quantity : 25PCS Model : P-TEC-2

- Sample Receiving Date : 2020-09-14 - Report Date : 2020-09-18 - The original sample is sticked on the last paper.

Test Performed

Judgement according to:N/A

Selected test(s) as requested by applicants. For details, refer to attached page(s).

Pronounce

The results shown in this report refer only to sample(s) tested unless otherwise stated.

All the items are performed in the standard conditions, except the noted cases.

Except for the requirement of the client, the test results and the conformity judgement of this report do not take the uncertainty of the test results into account.

Signed for and on behalf of

CNTAC Testing Service Co.,Ltd.(Foshan)

Approved by



Testing Report	Security website: www.fcl-sz.org.cn Security code: 7167787160	
Report No: ZFLJ2647747A	Page 2 of 3	



--- Test Result ---

1. / EN 13274-7:2019

Air flow: 95L/min, Aerosol: NaCl.

Unit: <%>

A.R.

sample 1#	83.8
sample 2#	88.0
sample 3#	81.7
S.W.	
sample 1#	73.0
sample 2#	75.8
sample 3#	74.3
M.S.+T.C.	
sample 1#	81.8
sample 2#	82.8
sample 3#	80.8
Maximum	88.0

Remark: 1. A.R.=As received, M.S.=Mechanical strength, S.W.=Simulated wearing treatment,

T.C.=Temperature conditioned

A.R. / S.W.: Average penetration over a time of 30s, beginning 3 min after the start of the test reported, M.S.+T.C.: Max. penetration during exposure test reported.

2. Permeability ISO 9237:1995

Test Area: 20cm2, Pressure Differencel: 100Pa.

Unit: <mm/s>

Result 162





Testing Report	Security website: www.fcl-sz.org.cn Security code: 7167787160	
Report No: ZFLJ2647747A	Page 3 of 3	



Original Sample

